September 2025

Aikon® AR 3023

2-sides coated abrasion-resistant extruded acrylic sheet

Aikon® AR 3023 is a clear transparent hard coated extruded acrylic sheet, which offers good optical clarity combined with the glass-like abrasion-resistance from the thermally cured hard coating.

Acrylic material by standard has a very high resistance against UV-radiation, which is further improved with the hard coating, offering a very long lifetime against UV-radiation.

BENEFITS

glass-like abrasion resistance superior UV resistance good chemical resistance good impact resistance

APPLICATIONS

health protection partition walls shop fittings furniture

PHYSICAL	Test Conditions	Typical values(1)	Unit	Standard
Density	ISO 1183	1,2	g/cm3	
Water Absorption	water at 23 °C	0.3	%	ISO 62
MECHANICAL				
Tensile Strength		70	MPa	ISO 527-2
Elongation at break		4	%	ISO 527-2
Tensile Modulus		3300	MPa	ISO 527-2
Flexural Strength		104	MPa	ISO 178
Flexural Modulus		3000	MPa	ISO 178
Rockwell Hardness		100	-	M scale
Taber abrasion resistance (2)	Δ haze after 500 cycles (500 g CS 10F)	2-8	%	ASTM D1044
Thermal				
Vicat Softening Temperature	50 N, 50°C/h	105-112	°C	ISO 306
Heat Deflection Temperature	1.82 Mpa	105	°C	ISO 75-1
Coefficient of linear thermal expansion	0-50°C	7x10-5	°K -1	
Thermal Conductivity		0.19	W/mK	ASTM C177
Electrical				
Dielectric Strength		20-25	kV/mm	DIN 53481
Dielectric Constant (50Hz)		3.6		DIN 53483
Dissipation Factor tanδ (1 MHz)		0.06		DIN 53483
Surface Resistivity		>1015	Ohm	IEC 60093
Volume Resistivity		>1015	Ohm.cm	IEC 60093

⁽¹⁾ These values are measured on injection moulded samples by the sheet manufacturer, and are not intended for specification purposes.

(2) Measured in-house according to ASTM D1044

Optical

Aikolon Oy Posankuja 3 90620 OULU – FINLAND VAT FI10666578 Tel: +358 207 7900 40 E-mail: <u>sales@aikon.fi</u>

Web: www.aikon.fi





PRODUCT DATASHEET

September 2025

Refractive Index		1.49		ISO 489
Light Transmission	3mm transparent sheet	92	%	ASTM D1003
Haze	3mm transparent sheet	< 1	%	

Impact Resistance

Charpy impact strenght	unnotched	15	kJ/m2	ISO 179/1fu
Izod impact strenght	notched	1.5	kJ/m2	ISO 180/1A

Permanent Service Temperature:

The permanent service temperature without load is approx. -40°C - +70°C continuous, +90°C short term.

Fire Behaviour

UL94 fire rating HB

Delivery formats

Aikon® AR 3023 is available in clear transparent colour and in thicknesses from between 3-15mm. Available in size 3000 x 2000mm. Other sizes, colours, and sheet thicknesses on request.

The manner in which you use and the purpose to which you put and utilize our products, technical assistance and information (whether verbal, written or by way of production evaluations), including any suggested formulations and recommendations, are beyond our control. Therefore, it is imperative that you test our products, technical assistance, information, and recommendations to determine to your own satisfaction whether our products, technical assistance and information are suitable for your intended uses and applications. This application-specific analysis must at least include testing to determine suitability from a technical as well as health, safety, and environmental standpoint. Such testing has not necessarily been done by Aikolon Oy. Unless we otherwise agree in writing, all products are sold strictly pursuant to the terms of our standard conditions of sale which are available upon request. All information and technical assistance are given without warranty or guarantee and is subject to change without notice. It is expressly understood and agreed that you assume and hereby expressly release us from all liability, in tort, contract or otherwise, incurred in connection with the use of our products, technical assistance, and information. Any statement or recommendation not contained herein is unauthorized and shall not bind us. Nothing herein shall be construed as a recommendation to use any product in conflict with any claim of any patent relative to any material or its use. No license is implied or in fact granted under the claims of any patent. Aikon® is a registered trademark of Aikolon Oy.

Aikolon Oy Posankuja 3 90620 OULU - FINLAND VAT FI10666578

Tel: +358 207 7900 40 E-mail: sales@aikon.fi

Web: www.aikon.fi

